

Premier Butyl™ S43 Innerwrap

Cold applied anti-corrosion and mechanical protection tape

Composition

Premier Butyl™ S43 Innerwrap is comprised of a polyethylene film coated on both sides with a butyl rubber compound.

Uses

Premier Butyl™ S43 Innerwrap can be used as anti-corrosion and mechanical protection around buried or immersed pipelines as well as welded seams. The Premier Butyl™ Tape System meets the requirements for class C according to DIN EN 12068 for temperatures up to 50°C as tested by DVGW.

Application

See *Instructions for use* for additional information. Premier Butyl™ S43 Innerwrap is part of the Premier Butyl™ Tape System and recommended to be used in conjunction with Premier Butyl™ P16HT Primer and Premier Butyl™ R23 Outerwrap.

Availability

Premier Butyl™ S43 Innerwrap is supplied in 15 m and 30 m rolls with widths ranging between 30 mm and 100 mm.

Storage Conditions

Store in a cool and dry place in original packaging.

Waste Material

Please do not discard waste material, including packaging, in the surrounding environment. Please follow all relevant legislation for disposal.

Typical properties

Premier Butyl™ S43 Innerwrap		
Thickness		
Adhesive		
Inside (grey)	≥0.51 mm	ASTM D1000
Outside	≥0.05 mm	
Backing	≥ 0.19 mm	
Total	≥0.75 mm	
Tape strength	≥10 N/mm ≥45 MPa	DIN EN 12068, ASTM D 1000
Elongation at break	≥750 % ≥800 %	DIN EN 12068 ASTM D 1000
Water absorption	≤0.05 %	ASTM D540
Shore D Hardness (PE film)	≥54	DIN 53505, ISO 868
Peel strength	23°C 50°C	
Tape to tape @ 100mm/min	≥4.0 N/mm ≥0.2 N/mm	DIN EN 12068
Tape to tape @ 100mm/min	≥4.0 N/mm ≥0.2 N/mm	ASTM D 1000
Tape to tape @ 300mm/min	≥5.0 N/mm ≥0.5 N/mm	ASTM D 1000
Ageing resistance		
Change in elongation at break after 100d, 70°C	- 3 %	DIN EN 12068
Change in tape strength after 100d, 70°C	- 3 %	ISO 21809-3
Change in peel str. Tape/tape after 100d, 70°C	<2 %	

Premier Butyl™ S43 Innerwrap

Premier Butyl™ Tape System		
Impact resistance	≥15 J ≥5.7 J/mm	DIN EN 12068 ISO 21809-3
Indentation resistance	23°C 50°C	
Pressure	10 N/mm ² 10 N/mm ²	DIN EN 12068
Residual layer thickness	≥0.9 mm ≥0.6 mm	ISO 21809-3
Specific electric insulation resistance	>10 ¹¹ Ωm ²	DIN EN 12068 ISO 21809-3
Dielectric strength	≥40 kV/mm	ASTM D149
Cathodic disbondment, 28d	23°C 50°C ≤8 mm ≤15 mm	DIN EN 12068 ISO 21809-3
Peel strength	23°C 50°C	
Outer tape to inner tape @ 100 mm/min	≥2.0 N/mm ≥0.2 N/mm	DIN EN 12068
On pipe surface @ 10mm/min	≥1.5 N/mm ≥0.2 N/mm	DIN EN 12068
On factory coating @ 10mm/min	≥1.8 N/mm ≥0.2 N/mm	DIN EN 12068
Outer tape to inner tape @ 100mm/min	≥2.0 N/mm ≥0.2 N/mm	ISO 21809-3
On pipe surface @ 10mm/min	≥1.8 N/mm ≥0.2 N/mm	ISO 21809-3
On factory coating @ 10mm/min	≥1.8 N/mm ≥0.2 N/mm	ISO 21809-3
On pipe surface after hot water, 28d @ 50°C	≥1.5 N/mm ≥0.2 N/mm	ISO 21809-3
On factory coating after hot water, 28d @ 50°C	≥2.0 N/mm ≥0.2 N/mm	ISO 21809-3
Outer tape to inner tape @ 300mm	≥2.0 N/mm ≥0.5 N/mm	ASTM D 1000
On pipe surface @ 300mm/min	≥4.0 N/mm ≥0.5 N/mm	ASTM D 1000
On factory coating @ 300mm/min	≥2.0 N/mm ≥0.5 N/mm	ASTM D 1000
Lap shear strength	23°C 50°C	
On steel @ 10mm/min	≥0.1 N/mm ² ≥0.05 N/mm ²	DIN EN 12068
On factory coating @10mm/min	≥0.1 N/mm ² ≥0.05 N/mm ²	DIN EN 12068
On steel @ 10mm/min	≥0.1 N/mm ² ≥0.05 N/mm ²	ISO 21809-3
On factory coating @ 10mm/min	≥0.1 N/mm ² ≥0.05 N/mm ²	ISO 21809-3
On factory coating @ 1.3mm/min	≥0.05 N/mm ² ≥0.05 N/mm ²	ASTM D 1000
Ageing resistance	≤10%	DIN EN 12068 ISO 21809-3
Change in peel str. To pipe surface 100d, 70°C		

Note: Premier Butyl™ Tape System is not suitable for the sealing of leakages in media transporting pipelined but exclusively for the prevention and protection from corrosion.

Important: Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. FM01548) and an Environmental Management System registered to BS EN 14001 (BSI Certificate 583748).

Page 2 of 2
Revision date: 04/12/2018

Winn & Coales (Denso) Ltd
Denso House, Chapel Road,
London SE27 0TR, United Kingdom



Tel: +44 (0) 20 8670 7511
Fax: +44 (0) 20 8761 2456
Email: mail@denso.net Web: www.denso.net